

SPHERO™ Magnetic Particles

- SPHERO™ Magnetic Microparticles provide high quality and reproducible results for your application
- Allow for rapid and reliable binding between the target and magnetic particle
- Consists of a uniform, monodispersed surface for optimal performance.

The SPHERO™ Magnetic Particles (Paramagnetic Particles) are prepared by coating a layer of iron oxide and polystyrene onto polystyrene core particles. The SPHERO™ Magnetic Particles are relatively uniform in size, spherical in shape and paramagnetic in nature. The paramagnetic nature of the particles allows them to be separated using a magnet and resuspended easily when removed from the magnet. They do not retain any significant magnetism even after repeat exposure to strong magnetic fields.

The SPHERO™ Smooth Surface Magnetic Particles have a thick layer of polymer coating on the surface of the particles to fully encapsulate the iron oxide coating. There is no exposed iron oxide on the surface of the particles. These particles are paramagnetic. The SPHERO™ Smooth Surface Magnetic Particles are particularly useful in applications where exposed iron oxide may interfere with the enzymatic activities or cause other undesirable interferences. The SPHERO™ Magnetic Particles are used for cell separation, affinity purification, DNA probe assays, magnetic particle EIA, etc.

The SPHERO™ Cross-linked Magnetic Particles are prepared to render them resistant to common organic solvents such as acetone, acetonitrile, DMF and chloroform. The cross-linked magnetic particles have significantly greater surface area and higher magnetite content (~15%) compared to the 4.0 μm uniform magnetic particles. They are also paramagnetic. Large surface area combined with higher magnetite content make SPHERO™ Cross-linked Magnetic Particles ideal solid phase for use in cell separation, magnetic removal of microorganisms, viruses and cross reactants in serum, as well as, affinity purification applications.

Figure 95 Histograms of Cat. No. CM-60-10 (Carboxyl Magnetic Particles, 2.5% w/v, 7.1 μm , 10 mL).




Figure 96 SEM Photo of Spherotech Cat. No. CM-80-10 (Carboxyl Magnetic Particles, 1% w/v, 8.5 μm , 10 mL).




Figure 97 Representative Scanning Electron Microscope photos of SPHERO™ Magnetic Particles are shown below: (A) CM-30-10 at 2000X, (B) CM-40-10 at 1000X, (C) Cross section of SPHERO™ Magnetic Particles, dark specks in (C) are magnetite on the surface of core particles. The SEM photo of SPHERO™ Smooth Surface Magnetic Particles, CMS-40-10, is shown in (D) at 5000x.






Figure 98 Magnetic Characteristics of SPHERO™ Magnetic Particles and Ferromagnetic Particles.

The magnetic characteristics of magnetic particles are determined by measuring the magnetic Hysteresis Loop of magnetic particles with a magnetometer as shown below. The magnetic particles are subjected to an increasing magnetizing field (H in Oersteds) in one direction, while sensing the magnetic field (B in Gauss) in the sample to reach maximum or saturation magnetization (B_m). The magnetizing field is then returned to zero and the field retained is measured as the remnant magnetization (B_r). Finally, the field is reversed until magnetization is at zero again. The corresponding field strength (H_c) is the coercivity of the magnetic particles. If the B_r and H_c are near zero, the magnetic particles are characterized as superparamagnetic as shown in (A). On the other hand, the Ferromagnetic Particles will have Hysteresis Loop similar to (B).

(A) Cat. No. CM-10-10 showing superparamagnetic characteristics.



(B) Cat. No. CFM-40-10 showing ferromagnetic characteristics.



SPHERO™ Magnetic Polystyrene Particles

- Consists of paramagnetic particles prepared by coating a layer of iron oxide and polystyrene onto polystyrene core particles
- Uniform in size and spherical in shape
- Separated using a magnet and resuspended when removed from the magnetic field
- Used for cell separation, affinity purification, DNA probe assays, magnetic particle EIA, etc.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Magnetic Polystyrene	2.0-2.9	2.5	PM-20-10	10 mL
Magnetic Polystyrene	2.0-2.9	2.5	PM-20-100	100 mL
Magnetic Polystyrene	3.0-3.9	2.5	PM-30-10	10 mL
Magnetic Polystyrene	3.0-3.9	2.5	PM-30-100	100 mL
Magnetic Polystyrene	4.0-4.5	2.5	PM-40-10	10 mL
Magnetic Polystyrene	4.0-4.5	2.5	PM-40-100	100 mL
Magnetic Polystyrene	5.0-5.9	2.5	PM-50-10	10 mL
Magnetic Polystyrene	5.0-5.9	2.5	PM-50-100	100 mL

SPHERO™ Carboxyl Magnetic Particles

- Used during the isolation and affinity purification of biomolecules in a wide range of assays and applications
- Contain carboxylic acid groups which can be used for carbodiimide activation (e.g. EDC) for covalent coupling
- Couple to the primary amino groups of nucleic acids, peptides, proteins or other target molecules.

For more information on Spherotech magnetic beads go to: www.Spherotech.com/pdetail.htm and select **Magnetic Particles**.



Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Carboxyl Magnetic	0.1-0.39	2.5	CM-025-10	10 mL
Carboxyl Magnetic	0.4-0.69	2.5	CM-05-10	10 mL
Carboxyl Magnetic	0.7-0.9	2.5	CM-08-10	10 mL
Carboxyl Magnetic	1.0-1.4	2.5	CM-10-10	10 mL
Carboxyl Magnetic	1.0-1.4	2.5	CM-10-100	100 mL
Carboxyl Magnetic	1.5-1.9	2.5	CM-15-10	10 mL
Carboxyl Magnetic	1.5-1.9	2.5	CM-15-100	100 mL
Carboxyl Magnetic	2.0-2.9	2.5	CM-20-10	10 mL
Carboxyl Magnetic	2.0-2.9	2.5	CM-20-100	100 mL
Carboxyl Magnetic	3.0-3.9	2.5	CM-30-10	10 mL
Carboxyl Magnetic	3.0-3.9	2.5	CM-30-100	100 mL
Carboxyl Magnetic	4.0-4.5	2.5	CM-40-10	10 mL
Carboxyl Magnetic	4.0-4.5	2.5	CM-40-100	100 mL
Carboxyl Magnetic	5.0-5.9	2.5	CM-50-10	10 mL
Carboxyl Magnetic	6.0-8.0	2.5	CM-60-10	10 mL
Carboxyl Magnetic	6.0-8.0	2.5	CM-60-100	100 mL
Carboxyl Magnetic	8.0-9.9	2.5	CM-80-10	10 mL
Carboxyl Magnetic	10.0-13.9	1.0	CM-100-10	10 mL
Carboxyl Magnetic	14.0-17.9	1.0	CM-150-10	10 mL
Carboxyl Magnetic	18.0-22.9	1.0	CM-200-10	10 mL
Carboxyl Magnetic	27.0-37.0	1.0	CM-300-10	10 mL
Carboxyl Magnetic	90.0-120.0	1.0	CM-1000-10	10 mL

SPHERO™ Jeffamine® Magnetic Particles

Contains a PEG-based spacer arm that is terminated with amine groups for coupling carboxyl-containing molecules.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Jeffamine® Magnetic	0.1-0.39	1.0	JAM-025-10	10 mL
Jeffamine® Magnetic	3.0-3.9	2.5	JAM-30-10	10 mL
Jeffamine® Magnetic, Smooth Surface	3.0-3.9	2.5	JAMS-30-10	10 mL

JEFFAMINE® is a registered trademark of Huntsman Corporation

SPHERO™ Amino Magnetic Particles

- Supplied as an aqueous suspension of magnetic iron oxide particles coated to provide primary amino groups
- Used to covalently couple proteins using bifunctional crosslinking agents
- Rapidly separates bound from unbound molecules using a magnetic separator due to paramagnetic properties.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Amino Magnetic	1.0-1.4	2.5	AM-10-10	10 mL
Amino Magnetic	1.0-1.4	2.5	AM-10-100	100 mL
Amino Magnetic	1.5-1.9	2.5	AM-15-10	10 mL
Amino Magnetic	1.5-1.9	2.5	AM-15-100	100 mL
Amino Magnetic	2.0-2.9	2.5	AM-20-10	10 mL
Amino Magnetic	2.0-2.9	2.5	AM-20-100	100 mL
Amino Magnetic	3.0-3.9	2.5	AM-30-10	10 mL
Amino Magnetic	3.0-3.9	2.5	AM-30-100	100 mL
Amino Magnetic	4.0-4.9	2.5	AM-40-10	10 mL
Amino Magnetic	4.0-4.9	2.5	AM-40-100	100 mL
Amino Magnetic	6.0-6.9	1.0	AM-60-10	10 mL
Amino Magnetic	6.0-6.9	1.0	AM-60-100	100 mL
Amino Magnetic	8.0-9.9	1.0	AM-80-10	10 mL

SPHERO™ Magnetic Cross-linked Particles


- Contains a very high magnetic content for fast magnetic response time
- Have high binding capacities due to their large surface area
- Resistant to common organic solvents such as acetone, acetonitrile, DMF and chloroform
- Used in a wide variety of molecular biology, nucleic acid isolation, research protocols and clinical immunoassay reagent applications.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Magnetic, Cross-linked, granules, non-uniform	3.0-6.0	2.5	PMX-40-10	10 mL
Amino Magnetic, Cross-linked	1.0-2.0	2.5	AMX-10-10	10 mL
Amino Magnetic, Cross-linked	1.0-2.0	2.5	AMX-10-100	100 mL
Amino Magnetic, Cross-linked	3.0-3.9	2.5	AMX-30-10	10 mL
Amino Magnetic, Cross-linked, granules, non-uniform	3.0-6.0	2.5	AMX-40-10	10 mL
Amino Magnetic, Cross-linked	13.0-17.99	1.0	AMX-150-5	5 mL
Carboxyl Magnetic, Cross-linked	1.0-2.0	2.5	CMX-10-10	10 mL
Carboxyl Magnetic, Cross-linked	1.0-2.0	2.5	CMX-10-100	100 mL
Carboxyl Magnetic, Cross-linked, granules, non-uniform	3.0-6.0	2.5	CMX-40-10	10 mL

SPHERO™ Diethylamino Magnetic Particles

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Diethylamino Magnetic	3.0-3.9	2.5	DEM-30-10	10 mL


Figure 99 Illustration of a DEAEMA magnetic particle.



SPHERO™ Dimethylamino Magnetic Particles

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Dimethylamino Magnetic	3.0-3.9	2.5	DM-30-10	10 mL

Figure 100 Illustration of a DMAEMA magnetic particle.



SPHERO™ Magnetic Polystyrene Particles, Smooth Surface

- Consists of a thick layer of polymer coating on the surface to encapsulate the iron oxide coating
- No exposed iron oxide on the surface
- Used in applications where exposed iron oxide causes undesirable interferences.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Magnetic Polystyrene , Smooth Surface	2.0-2.9	2.5	PMS-20-10	10 mL
Magnetic Polystyrene , Smooth Surface	2.0-2.9	2.5	PMS-20-100	100 mL
Magnetic Polystyrene , Smooth Surface	3.0-3.9	2.5	PMS-30-10	10 mL
Magnetic Polystyrene , Smooth Surface	3.0-3.9	2.5	PMS-30-100	100 mL
Magnetic Polystyrene , Smooth Surface	4.0-5.0	2.5	PMS-40-10	10 mL
Magnetic Polystyrene , Smooth Surface	4.0-5.0	2.5	PMS-40-100	100 mL

SPHERO™ Amino Magnetic Particles, Smooth Surface

- NEW - SPHERO™ Amino High Magnetic Content Microparticles
- Aids in the separation in whole blood
- Monodispersed surface for optimal performance.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Amino Magnetic, Smooth Surface	4.0-5.0	2.5	AMS-40-10	10 mL
Amino Magnetic, Smooth Surface	4.0-5.0	2.5	AMS-40-100	100 mL
Amino Magnetic, Smooth Surface, High Iron	4.0-5.0	2.5	AMS-40-10H	10 mL

SPHERO™ Carboxyl Magnetic Particles, Smooth Surface

- Activated for covalent coupling to amine-containing molecules using a variety of mechanisms
- Used with one or two-step coupling using EDC to form amide bonds with proteins or other molecules
- Used for coupling to amino modified oligonucleotide probes with MES buffer and EDC.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Carboxyl Magnetic, Smooth Surface	3.0-3.9	2.5	CMS-30-10	10 mL
Carboxyl Magnetic, Smooth Surface	3.0-3.9	2.5	CMS-30-100	100 mL
Carboxyl Magnetic, Smooth Surface	4.0-5.0	2.5	CMS-40-10	10 mL
Carboxyl Magnetic, Smooth Surface	4.0-5.0	2.5	CMS-40-100	100 mL
Carboxyl Magnetic, Smooth Surface	8.0-9.9	1.0	CMS-80-10	10 mL
Carboxyl Magnetic, Smooth Surface	18.0-22.9	1.0	CMS-200-10	10 mL

SPHERO™ Hydroxyethyl Magnetic Particles, Smooth Surface

- Contains primary hydroxyls on the surface
- Exhibits hydrophilic characteristics
- Activated for covalent coupling using epoxy and vinyl sulfone activation procedures
- Used for the coupling to amine-, thiol-, or hydroxyl-containing ligands.

Particle Type and Surface	Size, μm	% w/v	Catalog No.	Unit
Hydroxyethyl Magnetic, Smooth Surface	3.0-3.9	2.5	HEMS-30-10	10 mL